



KECK-COLOURPASTE TYPE 1902/300 white uv-stabilized

Application : Colouring of Polyether – and Polyester-Polyurethane foams.
KECK-Colourpaste 1902/300 white uv-stabilized distinguishes by a very good pigment stability and uv-stability. If stored over a longer period, the Colourpaste should be stirred again shortly before processing.

Processing : **KECK-Colourpaste 1902/300** is inserted into the mixing head by means of a metering device. It is added to the Polyurethane-components A+B.
The Colourpaste should be stirred during storage in the dosage unit in order to avoid fluctuation in the colour shades with the ready-to-use product.
The viscosity of the **Pigment-Paste 1902/300** is at approximately 3500 mPas/20°C, it is therefore suitable for the metering devices that are used in the market.
The additional quantity is between 2 to 4% calculated from the polyol (Comp.A).

Technical Data : - Base : Anorganic and organic pigments dispersed in plasticizers and polyols.

- Viscosity : 2,4 g/cm³
- Hazardous Classification : None
- Flashpoint : None
- Storage : Cool, and dry.

The information contained herein is based on our technical knowledge and experience. Since it is the user's responsibility to determine the suitability of the product for his own use, he should thoroughly test any application.