



HARDENER 859

Application : The hardener 859 is used for cross-linking of adhesives based on Polyurethane-dispersions.

The additional quantity to the ready to use adhesive is 5 %.

Technical Data	:	- Base	:	Aliphatic polyisocyanate
		- Density	:	1,15 g/cm ³
		- Hazardous Classification	:	None
		- Flashpoint	:	None
		- Storage	:	Approximately 6 months.
		- Packing	:	1 kg - tin drums.

The Keck- Hardener 859 has to be stirred during the mixing process with the adhesive and has to be stirred until a complete homogeneity is granted.

The pot-life of the mixture is 1 working – day.

09.09.2016

The information contained herein is based on our technical knowledge and experience. Since it is the user's responsibility to determine the suitability of the product for his own use, he should thoroughly test any application.